



Outlined below is the rating **INNOVATIVE COMPOSITES** products received in the testing for stain and heat resistance. With 1(one) being the highest rating out of 10 for compliance for Australian Standards, Innovative Composites have developed materials that are high performing and extremely durable surface.

AUSTRALIAN STANDARD 2924.2 –1998

REAGENTS	RATING
Group 1 (24 Hours)	
ACETONE	1
DETERGENT	1
MUSTARD	1
TRICHLOROETHANE	1
WATER	1
Group 2 (16 Hours)	
AMMONIA (10%)	1
COFFEE @ 80 D/CELSIUS	1
LIPSTICK	1
SODIUM TETRAPHOSPHATE	1
UREA	1
BLUING AGENT	1
TOLUENE	1
WATER BASED INK	1
GENTIAN VIOLET	1
Group 3 (10 Minutes)	
ACETIC ACID (30%)	1
HYDROGEN PEROXIDE (30%)	1
IODINE	1
MERCUROCHROME	1
SHOE POLISH	1
SODIUM HYDROXIDE (25%)	1
Group 4 (20 Minutes)	
CITRIC ACID (10%)	1

CONCLUSION:

The supplied polyester resin panels conform to the stain resistance requirements outlined in the Australian Standard for High Pressure Decorative Laminates. Neither panel showed any discolouration or surface degradation with any of the reagents used.